

Insulflow Marine | Pour-in-Place Foam

Product Description

Insulflow Marine is a closed cell, medium-density, two-component rigid polyurethane pour foam. Insulflow Marine is HFO-based and complies with Montreal Protocol blowing agent regulations. It has superior insulation properties and is formulated as a pour-in-place system for marine applications and general cavity fill. Insulflow Marine conforms to the US Coast Guard standard 183.114.

Recommended Uses

- Marine flotation
- Insulated panels and cavities
- General cavity fill

Storage

Store in a dry location between 50-90°F (10-32°C). Keep drums tightly sealed when not in use.

Processing Parameters

Insulflow Marine should be processed through a plural component system at a 1:1 ratio by volume. For hand mixing procedures, contact an Elastochem specialist for more details.

Attribute	Isocyanate	Resin
Mixing Ratio (volume)	100	100
Mixing Ratio (weight)	108	100
Pressure	1000-1500 psi	
Pre-Heater Temperature	95-105°F (35-40°C)	
Hose-Heater Temperature	95-105°F (35-40°C)	

Reactivity Profile

Attribute	Hand Mix
Cream Time	25-35 sec.
Gel Time	110-140 sec.
Tack Free Time	240-290 sec.
Free Rise Density	2.02-2.35 lbs/ft ³

DISCLAIMER: This data is based on information believed to be reliable and is offered solely for evaluation. Elastochem Specialty Chemicals Inc.'s products are sold with the understanding that clients do their own testing to determine the suitability of these products for their particular application. Since the use of this product is beyond the control of the Seller, the Buyer assumes all risks of use or handling, whether in accordance with directions or not, as the Seller makes no warranty, expressed or implied, concerning this product.



Elastochem Specialty Chemicals Inc.
37 Easton Road Brantford, ON N3P 1J4
1-877-787-2436
www.elastochem.com

Typical Properties

Attribute	Test	Results
Free-Rise Density	ASTM D1622	32.36 kg/m ³ (2.02 lbs/ft ³)
R-Value (90 Days)	ASTM C518	6.3 @ 1"
Compressive Strength	ASTM D1621	25 psi
Dimensional Stability @ 70°C, 97% RH @ 100°C @ -40°C	ASTM D2126	< 1% change
Tensile Strength	ASTM D1623	210 kPa (30 psi)
Closed Cell Content	ASTM D6226	92%

Liquid Component Properties

Attribute	Isocyanate	Resin
Colour	Brown	Clear/Yellow
Viscosity	250 cps	600-900 cps
Specific Gravity	1.24	1.12
Shelf Life	12 months	6 months
Storage Temperature	50-90°F (10-32°C)	50-90°F (10-32°C)

Summary of Buoyancy Test Results

Conforms to US Coast Guard Code Article 183.114

Procedure	24 Hours	30 Day
Immersion in gasoline	2.3%	2.5%
Immersion in bilge solution	1.6%	3.2%
Immersion in liquid B	2.1%	2.2%
Immersion in fully saturated gasoline vapour @ 38°C	n/a	2.0%

Health and Safety Information

Appropriate literature has been assembled which provides information concerning the health and safety precautions that must be observed when handling this product. Before working with this product, you must read and become familiar with the available information on its risks, proper use, and handling. This cannot be overemphasized. Information is available in several forms, e.g., safety data sheets and product labels. For further information contact your Elastochem Representative.

